



BESTON GROUP CO., LTD

9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER, ZHENGZHOU CITY, CHINA

WEB: www.bestongroup.com

裂解实验单/Pyrolysis Test

日期/Date: 2024/02/23

送样人/Sender: Mr. Feng

样品资料/Sample information:			
样品名称 Name	PP Granules	送样重量 Weight	/
样品状态 Sample status	/	取样重量 Sampling weight	200g
实验用时 Time	1h 30min	实验温度 Temperature	323°C
实验过程/Testing progress:			
序号 No.	时间段 Time	烟气温度 Flue gas temperature	备注 Remark
1	09:02	20°C	开始加热 Start heating
2	09:19	37°C	出烟 Smoke production
3	09:22	60°C	大量出烟 Heavy smoke production
4	09:29	138°C	出油 Oil production
5	09:35	196°C	出油加快 Oil production increases
6	09:55	323°C	/
7	10:02	261°C	出油减少 Oil production decreases
8	10:32	166°C	停止加热 Stop heating
实验结果/Result:			
项目 Item	组成 Composition	单位/g Unit/g	占比量/% Ratio/%
裂解试验 Pyrolysis testing	油 Oil	141.5g	70.75%
	渣 Residue	25.5g	12.75%
	气 Gas	33g	16.5%
实验总结 Test summary			
备注: 以上数据仅供参考 Noted: The above data is for reference only		签章/signature:	



BESTON GROUP CO., LTD

9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER, ZHENGZHOU CITY, CHINA
WEB: www.bestongroup.com

原料图片 Raw Material



油样图片 Oil Product



渣样图片 Solid Residue

