



BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

日期Date: 2025/11/12 **送样人Sender:** 冯超辉

样品资料/Sample information:

样品名称 Name	All-Steel Tire Granules	送样重量 Weight	—
样品状态 Sample status		取样重量 Sampling weight	300g
实验用时 Time	1H43min	实验温度 Temperature	325℃

实验过程Experimental process:

普通裂解

序号 No.	时间段 Time	烟气温度 Flue gas	备注 Remark
1	9:01	16℃	Start heating
2	9:13	31℃	Start emitting smoke
3	9:18	77℃	Oil starts to come out
4	9:19	91℃	Large amounts of smoke
5	9:21	98℃	Accelerate oil output
6	9:44	318℃	Oil output slows down
7	9:49	325℃	/
8	10:03	265℃	Stop oil discharge
9	10:44	168℃	Stop heating
10			
11			
12			

实验结果/Result:

项目 Item	组成 Composition	单位/g Unit/g	占比量/% Ratio/%
	Pyrolysis oil	129g	43.00%
	Carbon black	132g	44.00%
	Combustible gas	39g	13.00%

实验总结
Test summary

备注:
以上数据仅供参考
Noted:
The above data is for reference only

签章/signature:



BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

Raw material pictures



Oil sample pictures



Carbon black pictures

