



BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

日期Date: 2026/3/23

送样人Sender:

冯超辉

样品资料/Sample information:

样品名称 Name	Newly purchased tire granules	送样重量 Weight	—
样品状态 Sample status		取样重量 Sampling weight	300g
实验用时 Time	3H07min	实验温度 Temperature	304℃

实验过程Experimental process:

普通裂解

序号 No.	时间段 Time	烟气温度 Flue gas	备注 Remark
1	10:49	20℃	Start heating
2	11:26	96℃	Oil starts to comeout
3	11:37	132℃	Accelerate oil output
4	11:54	244℃	Start emitting smoke
5	12:00	277℃	Large amounts of smoke
6	12:14	304℃	/
7	12:25	300℃	Oil output slows down
8	12:34	295℃	Stop oil discharge
9	13:56	210℃	Stop heating
10			
11			
12			

实验结果/Result:

项目 Item	组成 Composition	单位/g Unit/g	占比量/% Ratio/%
	Pyrolysis oil	99g	33.00%
	Carbon black	170g	56.67%
	Combustible gas	31g	10.33%

实验总结
Test summary

备注:
以上数据仅供参考
Noted:
The above data is for reference only

签章/signature:




BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

Raw material pictures



Oil sample pictures



Carbon black pictures

