



BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

日期Date: 2026.04.16

送样人Sender: 靖钊辉

样品资料/Sample information:				
样品名称 Name	EFB-B		送样重量 Weight	—
样品状态 Sample status			取样重量 Sampling weight	200g
实验用时 Time	3H10min		实验温度 Temperature	239℃
实验过程Experimental process:			Carbonization	
序号 No.	时间段 Time	可燃气温度 Syngas temperature	物料温度 material temperature	备注 Remark
1	15:55	23℃	26℃	Start heat
2	16:14	93℃	111℃	Small syngas
3	16:15	99℃	125℃	Start generate oil
4	16:17	102℃	133℃	More syngas
5	16:22	131℃	176℃	Fastly generate oil
6	16:42	239℃	418℃	Slowly generate oil
7	16:43	235℃	437℃	
8	16:51	225℃	451℃	Stop generate oil
9	19:05	223℃	488℃	Stop heat
10				
11				
12				
实验结果/Result:				
项目 Item	组成 Composition	单位/g Unit/g	占比量/% Ratio/%	
	Wood vinegar and tar	97g	48.50%	
	Biochar	57g	28.50%	
	Syngas	46g	23.00%	
实验总结 Test summary				
备注: 以上数据仅供参考 Noted: The above data is for reference only			签章/signature: Mr. Li	




BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

Raw materials pictures



Wood vinegar and tar pictures



Biochar picturees

