



BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

日期Date: 2026.05.14

送样人Sender: 王梦雅

样品资料/Sample information:				
样品名称 Name	EFB		送样重量 Weight	—
样品状态 Sample status			取样重量 Sampling weight	120g
实验用时 Time	3H03min		实验温度 Temperature	198℃
实验过程Experimental process:			Carbonization	
序号 No.	时间段 Time	可燃气温度 Syngas temperature	物料温度 material temperature	备注 Remark
1	9:49	24℃	24℃	Start heat
2	10:03	66℃	148℃	Small syngas
3	10:04	87℃	200℃	Start generate oil
4	10:07	94℃	265℃	Fastly generate oil
5	10:11	93℃	384℃	More syngas
6	10:24	143℃	574℃	Slowly generate oil
7	10:35	159℃	600℃	Stop generate oil
8	11:26	198℃	634℃	
9	12:52	171℃	581℃	Stop heat
10				
11				
12				
实验结果/Result:				
项目 Item	组成 Composition	单位/g Unit/g	占比量/% Ratio/%	
	Wood vinegar and tar	52g	43.33%	
	Biochar	40g	33.33%	
	Syngas	28g	23.33%	
实验总结 Test summary				
备注: 以上数据仅供参考 Noted: The above data is for reference only			签章/signature: Mr. Li	




BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

Raw materials pictures



Wood vinegar and tar pictures



Biochar picturees

