



BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

日期Date: 2026.03.25

送样人Sender: 李东阳

样品资料/Sample information:				
样品名称 Name	木片		送样重量 Weight	——
样品状态 Sample status			取样重量 Sampling weight	150g
实验用时 Time	3H01min		实验温度 Temperature	200℃
实验过程Experimental process:			Carbonization	
序号 No.	时间段 Time	可燃气温度 Syngas temperature	物料温度 material temperature	备注 Remark
1	17:09	23℃	20℃	Start heat
2	17:24	57℃	80℃	Small syngas
3	17:28	90℃	106℃	More syngas
4	17:30	96℃	121℃	Start generate oil
5	17:38	97℃	236℃	Fastly generate oil
6	17:55	176℃	361℃	Slowly generate oil
7	18:01	200℃	425℃	
8	18:12	193℃	447℃	Stop generate oil
9	20:10	161℃	468℃	Stop heat
10				
11				
12				
实验结果/Result:				
项目 Item	组成 Composition	单位/g Unit/g	占比量/% Ratio/%	
	Wood vinegar and tar	78g	52.00%	
	Biochar	42g	28.00%	
	Syngas	30g	20.00%	
实验总结 Test summary				
备注: 以上数据仅供参考 Noted: The above data is for reference only			签章/signature: Mr. Li	



BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

Raw materials pictures



Wood vinegar and tar pictures



Biochar pictures

