



BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

日期Date: 2026/3/1 送样人Sender: 冯超辉

样品资料/Sample information:

样品名称 Name	Tire granules	送样重量 Weight	—
样品状态 Sample status		取样重量 Sampling weight	500g
实验用时 Time	2H58min	实验温度 Temperature	333℃

实验过程Experimental process:

普通裂解

序号 No.	时间段 Time	烟气温度 Flue gas	备注 Remark
1	9:00	12℃	Start heating
2	9:25	97℃	Oil starts to comeout
3	9:32	149℃	Start emitting smoke
4	9:34	165℃	Accelerate oil output
5	9:48	265℃	Large amounts of smoke
6	10:13	333℃	\
7	10:18	331℃	Oil output slows down
8	10:40	299℃	Stop oil discharge
9	11:58	199℃	Stop heating
10			
11			
12			

实验结果/Result:

项目 Item	组成 Composition	单位/g Unit/g	占比量/% Ratio/%
	Pyrolysis oil	186g	37.20%
	Carbon black	243g	48.60%
	Combustible gas	71g	14.20%

实验总结
Test summary

备注:
以上数据仅供参考
Noted:
The above data is for reference only

签章/signature:



BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

Raw material pictures



Oil sample pictures



Carbon black pictures

