BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

日期Date: 09/01/2026

样品资料/Sample information:				
样品名称 Name	棕榈叶		**送样重量 Weight**	——
样品状态 Sample status			**取样重量 Sampling weight**	100gg
实验用时 Time	2H47minmin		**实验温度 Temperature**	220°C
实验过程Experimental process:			**Carbonization**	
序号 No.	**时间段 Time**	**可燃气温度 Syngas temperature**	**物料温度 material temperature**	**备注 Remark**
1	15:00	15℃	14°C	Start heat
2	15:13	40℃	96℃	Small syngas
3	15:18	98℃	188℃	Start heat
4	15:22	98℃	296℃	Fastly generate oil
5	15:42	209℃	524℃	Slowly generate oil
6	15:49	220℃	540℃	
7	15:59	216℃	555℃	Stop generate oil
8	17:47	155℃	379℃	Stop heat
9				
10				
11				
12				

实验结果/Result:			
项目 Item	**组成 Composition**	**单位/g Unit/g**	**占比量/% Ratio/%**
	Wood vinegar and tar	42g	42.00%
	Biochar	33g	33.00%
	Syngas	25g	25.00%
实验总结 Test summary			

备注: **以上数据仅供参考** **Noted:** **The above data is for reference only**	**签章/signature: Mr. Li**

BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

Raw materials pictures



Wood vinegar and tar pictures



Biochar picturees

