BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

日期Date:	2025/12/15	**送样人Sender:**	张建坤

样品资料/Sample information:

样品名称 Name	油泥和塑料/ oil slusge and plastic	**送样重量 Weight**	——
样品状态 Sample status		**取样重量 Sampling weight**	150g
实验用时 Time	2H58min	**实验温度 Temperature**	347℃
实验过程Experimental process:		**普通裂解**	

序号 No.	**时间段 Time**	**烟气温度 Flue gas**	**备注 Remark**
1	10:47	19℃	Start Heating
2	10:57	32℃	Smoke
3	11:00	91℃	Oil starts to come out
4	11:01	100℃	Accelerate oil output
5	11:06	106℃	Reduced oil output
6	12:01	347℃	Oil output stopped
7	12:01	347℃	\
8	13:45	180℃	Stop heating

实验结果/Result:

项目 Item	**组成 Composition**	**单位/g Unit/g**	**占比量/% Ratio/%**
	Oil	37g	24.67%
	Slag	38g	25.33%
	Combustible gas	42g	28.00%
	Water	33g	22.00%
实验总结 Test summary			

备注: **以上数据仅供参考** **Noted:** **The above data is for reference only**	**签章/signature:**

BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

Raw material pictures



Oil sample pictures



Slag pictures



Water pictures

